

Condat digital gloss

Description:

Condat 2 side coated woodfree paper with high gloss and excellent smoothness for digital printing.

The reasons for the exceptional strength, smoothness and gloss of this coated paper are no secret. They lie in the choice of coating bases to reduce the degree of calendering and maintain paper bulk. Its smoothness means that dots remain closer to the paper surface for superlative high definition printwork.

Suitable and tested on leading digital inkjet presses. Certified for HP Indigo sheet-fed digital presses.

Available in a wide range of substances and formats, reels and sheets.

End uses:

Books, Brochures, Catalogues, Covers, Direct mail, Folders, Inserts, Postcards

Print methods:

Digital, HP Indigo, Inkjet

Certificates:

- [PEFC Chain of Custody \(multisite\)](#)
- [FSC Chain of Custody \(multisite\)](#)
- [HP Indigo - Digital Gloss 150gsm](#)
- [HP Indigo - Digital Gloss 170gsm](#)
- [HP Indigo - Digital Gloss 200gsm](#)
- [HP Indigo - Digital Gloss 250gsm](#)
- [HP Indigo - Digital Gloss 270gsm](#)
- [HP Indigo - Digital Gloss 300gsm](#)
- [HP Indigo - Digital Gloss 350gsm](#)
- [ISO 14001 Environment](#)
- [ISO 50001 Energy Efficiency](#)
- [ISO 9001 Quality](#)
- [ISO 45001 Health and Safety - Lecta](#)

For further details regarding compliance with food contact regulation, please contact our sales teams.

Condat digital gloss

Technical specifications

Property	Test Method	Unit	Tolerance	90	100	115	130	135	150	170	200	250	270	300	350
Substance	ISO 536 TAPPI T410	g/m ²	±4%	90	100	115	130	135	150	170	200	250	270	300	350
Bulk	ISO 534 TAPPI T411	cm ³ /g	±5%	0.76	0.76	0.78	0.74	0.74	0.73	0.74	0.74	0.76	0.76	0.77	0.81
Opacity	ISO 2471 TAPPI T519	%	-2.0	90.0	92.0	94.0	95.0	96.0	97.0	97.0	-	-	-	-	-
Whiteness D65/10°	ISO 11475	%	±3	120.0	120.0	120.0	120.0	120.0	120.0	120.0	120.0	120.0	120.0	120.0	120.0
Paper gloss	ISO 8254-1 TAPPI T480	%	±5	70	72	72	72	75	75	75	75	75	75	75	75
Bekk smoothness	ISO 5627 TAPPI T479	s	±30%	2200	2000	1600	1000	1000	1000	850	600	500	400	350	300
Relative humidity	TAPPI T502	%	±7	45	45	45	45	45	45	45	45	45	45	45	45

Storage recommendations

Ideally, the paper should be stocked in pressrooms conditioned to 48% (±5) relative humidity and 23°C (±2) temperature.

In any case, extremes of temperature and humidity must be avoided.

The technical properties of the product are guaranteed for 12 months after the production date.

Values are subject to change without notice.

Last update: 07/27/2026