

## Condat matt Périgord RO

### Description:

Condat 2 side coated woodfree paper with extraordinary bulk and an extra matt surface for heat set web offset printing.

Condat matt Périgord has always lived up to its reputation as a high bulk, extra matt paper. Its unique high-fibre composition gives it extraordinary bulk, meaning greater thickness for the same grammage or equal thickness with a lighter weight.

High whiteness, excellent runnability, quick ink set off and impressive printability on heat set web offset presses.

Available in a wide range of substances and formats, in sheets and reels.

### End uses:

Books, Brochures, Catalogues, Covers, Direct mail, Folders, Inserts, Packaging, Postcards

### Print methods:

Rotogravure, Offset

### Certificates:

- [PEFC Chain of Custody \(multisite\)](#)
- [FSC Chain of Custody \(multisite\)](#)
- [ISO 14001 Environment](#)
- [ISO 50001 Energy Efficiency](#)
- [ISO 9001 Quality](#)
- [ISO 45001 Health and Safety - Lecta](#)

For further details regarding compliance with food contact regulation, please contact our sales teams.

## Condat matt Périgord RO

### Technical specifications

| Property           | Test Method                | Unit             | Tolerance | 90    | 100   | 115   | 118   | 130   | 135   | 150   | 170   |
|--------------------|----------------------------|------------------|-----------|-------|-------|-------|-------|-------|-------|-------|-------|
| Substance          | ISO 536<br>TAPPI T410      | g/m <sup>2</sup> | ±4%       | 90    | 100   | 115   | 118   | 130   | 135   | 150   | 170   |
| Thickness          | ISO 534<br>TAPPI T411      | µm               | ±4%       | 93    | 104   | 123   | 102   | 140   | 147   | 156   | 182   |
| Opacity            | ISO 2471<br>TAPPI T519     | %                | -2.0      | 92.0  | 93.5  | 95.0  | 95    | 96.0  | 96.5  | 97.5  | 98.0  |
| Whiteness D65/10°  | ISO 11475                  | -                | ±3        | 121.4 | 121.4 | 121.4 | 121.4 | 121.4 | 121.4 | 121.4 | 121.4 |
| Bekk smoothness    | ISO 5627<br>TAPPI T479     | s                | ≤0.80*STD | -     | -     | -     | -     | 100   | 100   | 100   | 100   |
| Bendtsen roughness | ISO 8791-2<br>TAPPI UM-535 | ml/min           | ≤1.2*STD  | 100   | 100   | 100   | -     | -     | -     | -     | -     |
| Relative humidity  | TAPPI T502                 | %                | ±7        | 40    | 40    | 40    | 40    | 40    | 40    | 40    | 40    |

### Storage recommendations

Ideally, the paper should be stocked in pressrooms conditioned to 50% (±5) relative humidity and 23°C (±2) temperature.

In any case, extremes of temperature and humidity must be avoided.

The product properties are guaranteed for 12 months after the production date.

Values are subject to change without notice.

Last update: 07/27/2026