

CreatorDigital Gloss

Description:

Creator 2 side coated woodfree paper with high gloss and excellent quality for digital printing.

The Creator brand gloss paper has multiple features to ensure optimal printing quality: high whiteness, very good paper and ink gloss, excellent dot transfer, and high runnability.

Suitable and tested on leading digital inkjet presses. Certified for use on HP Indigo sheet-fed digital presses.

Available in a wide range of substances and formats, in sheets.

End uses:

Books, Brochures, Catalogues, Covers, Direct mail, Folders, Inserts, Postcards

Print methods:

Digital, HP Indigo, Inkjet

Certificates:

- [HP Indigo Digital Gloss 100gsm](#)
- [HP Indigo Digital Gloss 130gsm](#)
- [HP Indigo - Digital Gloss 150gsm](#)
- [HP Indigo - Digital Gloss 170gsm](#)
- [HP Indigo - Digital Gloss 200gsm](#)
- [HP Indigo - Digital Gloss 250gsm](#)
- [HP Indigo - Digital Gloss 300gsm](#)
- [HP Indigo - Digital Gloss 350gsm](#)
- [FSC Chain of Custody \(multisite\)](#)
- [REACH regulation Lecta](#)
- [ISO 14001 Environment](#)
- [ISO 50001 Energy Efficiency](#)
- [Paper Profile Creator - Motril](#)
- [Paper Profile Creator - Sant Joan les Fonts](#)
- [Paper Profile GardaMatt Card](#)
- [Paper Profile GardaMatt Card Digital](#)
- [Paper Profile GardaMatt Card Duo](#)
- [ISO 9001 Quality](#)
- [ISO 45001 Health and Safety - Lecta](#)

For further details regarding compliance with food contact regulation, please contact our sales teams.

CreatorDigital Gloss

Technical specifications

Property	Test Method	Unit	Tolerance	115	135	150	170	200	250	300	350
Substance	ISO 536 TAPPI T410	g/m ²	±4%	115	135	150	170	200	250	300	350
Thickness	ISO 534 TAPPI T411	µm	±4%	89	100	110	125	148	190	232	285
Opacity	ISO 2471 TAPPI T519	%	-2	93	95.5	96.5	97.0	-	-	-	-
Whiteness D65/10°	ISO 11475	-	±3	119	119	119	119	119	119	119	119
Paper gloss	ISO 8254-1 TAPPI T480	%	±5	72	72	74	74	74	74	74	74
Bekk smoothness	ISO 5627 TAPPI T479	s	±30%	1300	1000	1000	850	600	500	350	250
Brightness R457/D65	ISO 2470-2	%	±2	95	95	95	95	95	95	95	95
Relative humidity	TAPPI T502	%	±7	48	48	48	48	48	48	48	48

Storage recommendations

Ideally, the paper should be stocked in pressrooms conditioned to 48% (±5) relative humidity and 23°C (±2) temperature.

In any case, extremes of temperature and humidity must be avoided.

The product properties are guaranteed for 12 months after the production date.

Values are subject to change without notice.

Last update: 07/01/2026