

## CreatorGloss RH

### Description:

Creator 2 side coated woodfree paper with high gloss and excellent smoothness for rotogravure printing.

This Creator brand gloss paper has multiple features to ensure optimal printing quality: high whiteness, very good paper and ink gloss, excellent dot transfer, and high runnability.

Available in reels.

### End uses:

Books, Brochures, Catalogues, Covers, Direct mail, Folders, Inserts, Packaging, Postcards

### Print methods:

Rotogravure

### Certificates:

- [PEFC Chain of Custody \(multisite\)](#)
- [FSC Chain of Custody \(multisite\)](#)
- [REACH regulation Lecta](#)
- [ISO 14001 Environment](#)
- [ISO 50001 Energy Efficiency](#)
- [Paper Profile Creator - Motril](#)
- [Paper Profile GardaMatt Card](#)
- [Paper Profile GardaMatt Card Digital](#)
- [Paper Profile GardaMatt Card Duo](#)
- [ISO 9001 Quality](#)
- [ISO 45001 Health and Safety - Lecta](#)

For further details regarding compliance with food contact regulation, please contact our sales teams.

## CreatorGloss RH

### Technical specifications

| Property          | Test Method              | Unit             | Tolerance | 90   | 100  | 115  |
|-------------------|--------------------------|------------------|-----------|------|------|------|
| Substance         | ISO 536<br>TAPPI T410    | g/m <sup>2</sup> | ±4%       | 90   | 100  | 115  |
| Thickness         | ISO 534<br>TAPPI T411    | µm               | ±4%       | 66   | 73   | 84   |
| Opacity           | ISO 2471<br>TAPPI T519   | %                | -2.0      | 89.0 | 91.0 | 92.5 |
| Whiteness D65/10° | ISO 11475                | CIE              | ±3        | 109  | 109  | 109  |
| Paper gloss       | ISO 8254-1<br>TAPPI T480 | %                | ±5        | 76   | 76   | 76   |
| Bekk smoothness   | ISO 5627<br>TAPPI T479   | s                | ≥0.9*STD  | 2300 | 2300 | 1800 |
| Relative humidity | TAPPI T502               | %                | ±7        | 40   | 40   | 40   |

### Storage recommendations

Ideally, the paper should be stocked in pressrooms conditioned to 50% (±5) relative humidity and 23°C (±2) temperature.

In any case, extremes of temperature and humidity must be avoided.

The technical properties of the product are guaranteed for 12 months after the production date.

Values are subject to change without notice.

Last update: 04/07/2026