

CreatorSilk

Description:

Creator 2 side coated woodfree paper with a unique feel.

Renowned for its velvety silk feel, its silk finish ensures comfortable reading without unwanted reflections while preserving color richness. With high whiteness and good ink gloss, this Creator paper offers outstanding print results and excellent dot definition. Available in a wide range of substances and formats, in sheets and reels.

End uses:

Books, Brochures, Catalogues, Covers, Direct mail, Folders, Inserts, Packaging, Postcards

Print methods:

Flexo, Laser/Dry toner, Offset, Rotogravure

Certificates:

- [HP Indigo - Digital Silk Coated 400g](#)
- [PEFC Chain of Custody \(multisite\)](#)
- [FSC Chain of Custody \(multisite\)](#)
- [REACH regulation Lecta](#)
- [ISO 14001 Environment](#)
- [ISO 50001 Energy Efficiency](#)
- [Paper Profile Creator - Motril](#)
- [Paper Profile Creator - Sant Joan les Fonts](#)
- [Paper Profile GardaMatt Card](#)
- [Paper Profile GardaMatt Card Digital](#)
- [Paper Profile GardaMatt Card Duo](#)
- [ISO 9001 Quality](#)
- [ISO 45001 Health and Safety - Lecta](#)

For further details regarding compliance with food contact regulation, please contact our sales teams.

CreatorSilk

Technical specifications

Property	Test Method	Unit	Tolerance	90	100	115	125	130	135	150	170	200	225	250	270	300	350	380
Substance	ISO 536 TAPPI T410	g/m ²	±4%	90	100	115	125	130	135	150	170	200	225	250	270	300	350	380
Thickness	ISO 534 TAPPI T411	µm	±4%	79	87	99	107	111	115	131	152	181	210	239	263	299	358	394
Opacity	ISO 2471 TAPPI T519	%	-2.0	92.0	93.0	95.0	95.5	96.0	96.0	97	97.5	-	-	-	-	-	-	-
Brightness R457/D65	ISO 2470-2	%	±2	96.5	96.5	96.5	96.5	96.5	96.5	96.5	96.5	96.5	96.5	96.5	96.5	96.5	96.5	96.5
Whiteness D65/10°	ISO 11475	CIE	±3	121.3	121.3	121.3	121.3	121.3	121.3	121.3	121.3	121.3	121.3	121.3	121.3	121.3	121.3	121.3
Parker roughness	ISO 8791-4 TAPPI T555	µm	≤1.3*STD	1.8	1.8	1.8	1.8	1.8	1.6	1.6	1.6	1.6	1.6	1.6	1.8	1.8	2.1	2.1
Relative humidity	TAPPI T502	%	±7	50	50	50	50	50	50	50	50	50	50	50	50	50	50	50

Storage recommendations

Ideally, the paper should be stocked in pressrooms conditioned to 50% (±5) relative humidity and 23°C (±2) temperature.

In any case, extremes of temperature and humidity must be avoided.

The technical properties of the product are guaranteed for 12 months after the production date.

Values are subject to change without notice.

Last update: 04/07/2026