

CreatorStar

Description:

Creator 2 side coated woodfree paper with high gloss and excellent properties.

This Creator brand gloss paper has multiple features to ensure optimal print quality: high whiteness, very good paper and ink gloss, excellent dot transfer, and high runnability.

Available in a wide range of substances and formats, in sheets and reels.

End uses:

Books, Brochures, Catalogues, Covers, Direct mail, Folders, Inserts, Packaging, Postcards

Print methods:

Flexo, Laser/Dry toner, Offset, Rotogravure

Certificates:

- [PEFC Chain of Custody \(multisite\)](#)
- [FSC Chain of Custody \(multisite\)](#)
- [REACH regulation Lecta](#)
- [ISO 14001 Environment](#)
- [ISO 50001 Energy Efficiency](#)
- [Paper Profile Creator - Motril](#)
- [Paper Profile Creator - Sant Joan les Fonts](#)
- [Paper Profile GardaMatt Card](#)
- [Paper Profile GardaMatt Card Digital](#)
- [Paper Profile GardaMatt Card Duo](#)
- [ISO 9001 Quality](#)
- [ISO 45001 Health and Safety - Lecta](#)

For further details regarding compliance with food contact regulation, please contact our sales teams.

CreatorStar

Technical specifications

Property	Test Method	Unit	Tolerance	90	100	115	125	130	135	150	170	200	225	250	270	300	350	380
Substance	ISO 536 TAPPI T410	g/m ²	±4%	90	100	115	125	130	135	150	170	200	225	250	270	300	350	380
Thickness	ISO 534 TAPPI T411	µm	±4%	67	75	85	91	95	99	110	125	146	166	186	202	230	278	302
Opacity	ISO 2471 TAPPI T519	%	-2.0	90	91	93.5	93.5	95.0	95.5	96.5	97.0	-	-	-	-	-	-	-
Brightness R457/D65	ISO 2470-2	%	±2	95.2	95.2	95.2	95.2	95.2	95.2	95.2	95.2	95.2	95.2	95.2	95.2	95.2	95.2	95.2
Whiteness D65/10°	ISO 11475	CIE	±3	119.0	119.0	119.0	119.0	119.0	119.0	119.0	119.0	119.0	119.0	119.0	119.0	119.0	119.0	119.0
Paper gloss	ISO 8254-1 TAPPI T480	%	±5	70	70	70	70	70	70	70	72	72	72	72	72	72	72	72
Bekk smoothness	ISO 5627 TAPPI T479	s	±30%	1400	1100	950	1500	1450	1400	1300	1000	800	700	600	500	400	300	200
Relative humidity	TAPPI T502	%	±7	50	50	50	50	50	50	50	50	50	50	50	50	50	50	50

Storage recommendations

Ideally, the paper should be stocked in pressrooms conditioned to 50% (±5) relative humidity and 23°C (±2) temperature.

In any case, extremes of temperature and humidity must be avoided.

The technical properties of the product are guaranteed for 12 months after the production date.

Values are subject to change without notice.

Last update: 04/07/2026