

## GardaMatt Digital

### Descrizione:

La patinata senza legno Garda con superficie opaca a massima levigatezza per la stampa digitale.

Questo prodotto garantisce una buona resa in spessore, una straordinaria macchinabilità, un'alta rigidità, un'ottima stampabilità, un'elevata opacità e un'eccellente brillantezza di stampa.

Idoneo e testato sulle principali presse digitali inkjet. Certificato per l'uso su presse digitali sheet fed HP Indigo.

Disponibile in varie grammature, in formato e bobine.

### Applicazioni:

Libri, Brochure, Cataloghi, Copertine, Direct mail, Cartelle, Inserti, Cartoline postali

### Metodi di stampa:

Digitale, HP Indigo, Inkjet

### Certificazioni:

- [HP Indigo - Digital Silk Coated 104g](#)
- [HP Indigo - Digital Matt 125g](#)
- [HP Indigo - Digital Matt 148g](#)
- [HP Indigo - Digital Matt 150g](#)
- [HP Indigo - Digital Matt 216g](#)
- [HP Indigo - Digital Matt 220g](#)
- [HP Indigo - Digital Matt 250g](#)
- [HP Indigo - Digital Matt 251g](#)
- [HP Indigo - Digital Matt 270g](#)
- [HP Indigo - Digital Matt 275g](#)
- [HP Indigo - Digital Matt 297g](#)
- [HP Indigo - Digital Matt 300g](#)
- [HP Indigo - Digital Matt 325g](#)
- [HP Indigo - Digital Silk Coated 100g](#)
- [HP Indigo - Digital Silk Coated 110g](#)
- [HP Indigo - Digital Silk Coated 115g](#)
- [HP Indigo - Digital Silk Coated 118g](#)
- [HP Indigo - Digital Silk Coated 130g](#)
- [HP Indigo - Digital Silk Coated 135g](#)
- [HP Indigo - Digital Silk Coated 170g](#)
- [HP Indigo - Digital Silk Coated 200g](#)
- [HP Indigo - Digital Silk Coated 280g](#)
- [HP Indigo - Digital Silk Coated 350g](#)
- [HP Indigo - Digital Silk Coated 400g](#)
- [HP Indigo - Digital Silk Coated 89g](#)
- [HP Indigo - Digital Silk Coated 90g](#)
- [PEFC Chain of Custody \(multisite\)](#)
- [FSC Chain of Custody \(multisite\)](#)
- [Paper Profile Garda](#)
- [Paper Profile GardaRecycled Print](#)
- [Paper Profile Creator - Cartiere del Garda](#)
- [Dichiarazione REACH Lecta](#)

## GardaMatt Digital

- [ISO 14001 Ambiente](#)
- [ISO 50001 Energy Efficiency](#)
- [ISO 9001 Calidad](#)
- [ISO 45001 Salute e Sicurezza - Lecta](#)

Consultate il nostro team commerciale per le applicazioni finali che richiedono una certificazione specifica.

# GardaMatt Digital

## Specifiche tecniche

Proprietà	Standard	Unità	Tolleranza	90	100	115	130	135	150	170	200	250	270	300	350	400
Grammatura	ISO 536 TAPPI T410	g/m <sup>2</sup>	±4%	90	100	115	130	135	150	170	200	250	270	300	350	400
Spessore	ISO 534 TAPPI T411	µm	±4%	80	86	100	111	115	131	153	181	240	263	300	358	405
Volume	ISO 534 TAPPI T411	cm <sup>3</sup> /g	-	0.89	0.86	0.87	0.85	0.85	0.87	0.89	0.91	0.96	0.97	1.0	1.02	1.01
Opacità	ISO 2471 TAPPI T519	%	-2.0	92.0	93.0	95.0	96.0	96.0	97.0	97.5	-	-	-	-	-	-
Punto di bianco D65/10°	ISO 11475	CIE	±3	119	119	119	119	119	119	119	119	119	119	119	119	119
Lucido carta	ISO 8254-1 TAPPI T480	%	±5	23	25	25	25	25	30	40	40	30	30	30	30	30
Rugosità parker	ISO 8791-4 TAPPI T555	µm	≤1.30*STD	2.6	2.4	2.4	1.8	1.8	1.8	1.8	1.8	1.8	1.8	1.8	2.1	1.8
Umidità relativa	TAPPI T502	%	±7	48	48	48	48	48	48	48	48	48	48	48	48	48

### Consigli per lo stoccaggio

Idealmente, la carta dovrebbe essere immagazzinata in sale stampa condizionate al 48% (± 5) di umidità relativa e 23°C (± 2) di temperatura. In ogni caso, è necessario evitare valori estremi di temperatura e umidità.

Per le applicazioni a contatto con gli alimenti, le proprietà del prodotto, secondo le specifiche, sono garantite per 12 mesi dopo la data di produzione.

Valori soggetti a possibili modifiche senza alcun preavviso.

Ultimo aggiornamento: 01/07/2026