

GardaPat 11 Ivory

Description:

Garda 2 side coated woodfree paper, with an ivory shade and matt surface.

GardaPat 11 is a matt coated paper with a very high bulk (volume 1.1). Its unique high-fibre composition gives it an extraordinary bulk. It guarantees excellent printing results and outstanding print quality for both text and color images.

High bulk, excellent runnability, quick ink set off and impressive printability. Suitable and tested on leading digital inkjet presses.

Available in different substances and formats in sheets and reels.

End uses:

Catalogues, Brochures, Books, Folders, Covers, Inserts, Magazines

Print methods:

Flexo, Laser/Dry toner, Offset, Inkjet

Certificates:

- [PEFC Chain of Custody \(multisite\)](#)
- [FSC Chain of Custody \(multisite\)](#)
- [Paper Profile Garda](#)
- [Paper Profile GardaRecycled Print](#)
- [Paper Profile Creator - Cartiere del Garda](#)
- [REACH regulation Lecta](#)
- [ISO 14001 Environment](#)
- [ISO 50001 Energy Efficiency](#)
- [ISO 9001 Quality](#)
- [ISO 45001 Health and Safety - Lecta](#)

For applications that require specific certifications or approvals, please contact our sales teams.

GardaPat 11 Ivory

Technical specifications

| Property | Test Method | Unit | Tolerance | 115 | 130 | 150 | 250 |
|--------------------|--------------------------|------------------|-----------|------|------|------|------|
| Substance | ISO 536 TAPPI T410 | g/m ² | ±4% | 115 | 130 | 150 | 250 |
| Thickness | ISO 534 TAPPI T411 | µm | ±4% | 126 | 143 | 165 | 275 |
| Parker roughness | ISO 8791-4 TAPPI T519 | µm | ±1 | 4 | 4 | 4 | 4 |
| Opacity | ISO 2471 TAPPI T519 | % | -2.0 | 92.5 | 93.5 | 94.5 | 98.0 |
| Whiteness D65/10° | ISO 11475 | % | ±3 | 86 | 86 | 86 | 86 |
| Relative humidity | TAPPI T502 | % | ±7 | 50 | 50 | 50 | 50 |
| Taber stiffness CD | ISO 2493 TAPPI 489 | gf*cm | ≥0.75*STD | 3 | 5 | 9 | 45 |
| Taber stiffness MD | ISO 2493 TAPPI 489 | gf*cm | ≥0.75*STD | 5 | 8 | 15 | 80 |

Storage recommendations

Ideally, the paper should be stocked in pressrooms conditioned to 50% (±5) relative humidity and 23°C (±2) temperature.

In any case, extremes of temperature and humidity must be avoided.

The technical properties of the product are guaranteed for 12 months after the production date.

Values are subject to change without notice.

Last update: 04/07/2026