

## **Diva Art Duo**

### **Description:**

Diva Art Duo has been specially designed for creative uses of graphic and luxury packaging.

- Solid Bleached Sulphate (SBS) paperboard, certified FSC® C011032, PEFC available from production
- Two-side coated paperboard with a silk finish
- Excellent printability and brilliant color reproduction
- Exceptional cracking resistance
- Perfect folding characteristics
- Outstanding finishing and converting properties
- Good caliper and stiffness
- Consistent smoothness and whiteness

### **End uses:**

Books, Brochures, Covers, Direct mail, Folders, Folding materials, Inserts, Magazines, Packaging, Postcards, Tags

### **Print methods:**

Digital, Flexo, HP Indigo, Offset

### **Certificates:**

- [PEFC Chain of Custody \(multisite\)](#)
- [FSC Chain of Custody \(multisite\)](#)
- [REACH regulation Lecta](#)
- [ISO 14001 Environment](#)
- [ISO 50001 Energy Efficiency](#)
- [ISO 9001 Quality](#)
- [ISO 45001 Health and Safety - Lecta](#)

For further details regarding compliance with food contact regulation, please contact our sales teams.

## Diva Art Duo

### Technical specifications

| Property               | Test Method              | Unit             | Tolerance | 250 | 280 | 300 | 330 | 350 | 380 |
|------------------------|--------------------------|------------------|-----------|-----|-----|-----|-----|-----|-----|
| Substance              | ISO 536<br>TAPPI T410    | g/m <sup>2</sup> | ±5%       | 250 | 280 | 300 | 330 | 350 | 380 |
| Thickness              | ISO 534<br>TAPPI T411    | µm               | ±5%       | 272 | 311 | 338 | 378 | 405 | 440 |
| Brightness<br>R457/D65 | ISO 2470-2<br>TAPPI T452 | %                | ±2        | 102 | 102 | 102 | 102 | 102 | 102 |
| Whiteness<br>D65/10°   | ISO 11475<br>TAPPI T562  | CIE              | ±3        | 132 | 132 | 132 | 132 | 132 | 132 |
| Paper gloss            | ISO 8254-1<br>TAPPI T480 | %                | ±5        | 30  | 30  | 30  | 30  | 30  | 30  |
| Taber stiffness<br>MD  | ISO 2493<br>TAPPI T556   | mN               | -25%      | 114 | 132 | 203 | 284 | 345 | 406 |
| Taber stiffness<br>CD  | ISO 2493<br>TAPPI T556   | mN               | -25%      | 71  | 77  | 122 | 162 | 183 | 213 |
| Parker roughness       | ISO 8791-4<br>TAPPI T555 | µm               | ≤2.5      | 2   | 2   | 2   | 2   | 2   | 2   |
| Relative humidity      | TAPPI T502               | %                | ±7        | 50  | 50  | 50  | 50  | 50  | 50  |

## **Diva Art Duo**

### **Storage recommendations**

Paper dimensions are very sensible to humidity variations that is why we supply paper in waterproof packaging. Once the packaging is opened, a moisture exchange can take place between the paper and the environment.

Ideally, the paper should be stocked in pressrooms conditioned to 50% ( $\pm 5$ ) relative humidity and 23°C ( $\pm 2$ ) temperature. In any case, extremes of temperature and humidity must be avoided.

The technical properties of the product are guaranteed for 12 months after the production date.

Before starting a production run, check that the printability is correct on both sides of 30-50 sheets.

Values are subject to change without notice.

Last update: 04/27/2026