

Coral Book Inkjet Ivory

Description:

Coral Book Inkjet Ivory is an uncoated ivory paper developed for high-speed inkjet printing use.

Its surface is specially treated to ensure optimal ink anchorage, enabling consistent performance and high-quality print results.

It offers excellent image definition and outstanding print quality in both B/W and color applications. The paper also ensures reliable runnability and fast ink drying, a key factor in high-speed printing.

Available in reels. Suitable with the most inkjet printing presses.

End uses:

Books, Brochures, Catalogues, Covers, Direct mail, Folders, Inserts, Postcards

Print methods:

Inkjet

Certificates:

- [PEFC Chain of Custody \(multisite\)](#)
- [FSC Chain of Custody \(multisite\)](#)
- [ISO 14001 Environment](#)
- [ISO 50001 Energy Efficiency](#)
- [ISO 9001 Quality](#)
- [ISO 45001 Health and Safety - Lecta](#)

For further details regarding compliance with food contact regulation, please contact our sales teams.

Coral Book Inkjet Ivory

Technical specifications

Property	Test Method	Unit	Tolerance	70	80	90	100
Bendtsen roughness	ISO 8791-2 TAPPI UM-535	μm	±25	150	150	150	160
Bulk	ISO 534 TAPPI T411	cm ³ /g	-	1,20	1,20	1,20	1,20
Opacity	ISO 2471 TAPPI T519	%	-2	92	93,5	95	96
Relative humidity	TAPPI T502	%	±7	37	37	37	37
Substance	ISO 536 TAPPI T410	g/m ²	±4%	70	80	90	100
Taber stiffness CD	ISO 2493 TAPPI T556	gf*cm	≥ 0,75*STD	0,6	0,8	1,1	1,5
Taber stiffness MD	ISO 2493 TAPPI T556	gf*cm	≥ 0,75*STD	1,6	2	2,5	3
Thickness	ISO 534 TAPPI T411	μm	± 4 %	84	96	108	119

Storage recommendations

Ideally, the paper should be stocked in pressrooms conditioned to 50% (±5) relative humidity and 23°C (±2) temperature. In any case, extremes of temperature and humidity must be avoided.

The product's technical properties are guaranteed 12 months after production.

Values are subject to change without notice.

Last update: 07/27/2026