

Coral Book Inkjet White

Description:

Coral Book Inkjet White is an uncoated white paper developed for high-speed inkjet printing use.

Its surface is specially treated to ensure optimal ink anchorage, enabling consistent performance and high-quality print results.

It offers excellent image definition and outstanding print quality in both B/W and color applications. The paper also ensures reliable runnability and fast ink drying, a key factor in high-speed printing.

Available in reels. Suitable with the most inkjet printing presses.

End uses:

Books, Brochures, Catalogues, Covers, Direct mail, Folders, Inserts, Postcards

Print methods:

Inkjet

Certificates:

- [PEFC Chain of Custody \(multisite\)](#)
- [FSC Chain of Custody \(multisite\)](#)
- [ISO 14001 Environment](#)
- [ISO 50001 Energy Efficiency](#)
- [ISO 9001 Quality](#)
- [ISO 45001 Health and Safety - Lecta](#)

For further details regarding compliance with food contact regulation, please contact our sales teams.

Coral Book Inkjet White

Technical specifications

Property	Test Method	Unit	Tolerance	70	80	90	100	120
Bendtsen roughness	ISO 8791-2 TAPPI UM-535	µm	±25	150	150	150	160	170
Bulk	ISO 534 TAPPI T411	cm³/g	-	1,20	1,20	1,20	1,20	1,20
Opacity	ISO 2471 TAPPI T519	%	-2	92	93,5	95	96	98
Relative humidity	TAPPI T502	%	±7	37	37	37	37	37
Substance	ISO 536 TAPPI T410	g/m²	±4%	70	80	90	100	120
Taber stiffness CD	ISO 2493 TAPPI T556	gf*cm	≥ 0,75*STD	0,6	0,8	1,1	1,5	2,3
Taber stiffness MD	ISO 2493 TAPPI T556	gf*cm	≥ 0,75*STD	1,6	2	2,5	-	4
Thickness	ISO 534 TAPPI T411	µm	± 4 %	84	96	108	119	142
Tensile strength MD	-	-	-	-	-	-	3	-

Storage recommendations Ideally, the paper should be stocked in pressrooms conditioned to 50% (±5) relative humidity and 23°C (±2) temperature. In any case, extremes of temperature and humidity must be avoided.

The technical properties of the product are guaranteed for 12 months after the production date.

Values are subject to change without notice.
Last update: 07/27/2026